

Low VOC Asphalt Primer

Last updated: 02-08-2011

SECTION 1 - PRODUCT & COMPANY IDENTIFICATIONName: **Low VOC Asphalt Primer**Product Number: **707**Class: **Asphalt Cutback Black Liquid**

Company Address: 3131 N. Columbia Blvd., Portland, OR 97217-7472 • P.O. Box 17217, Portland, OR 97217 -0217

Telephone: (503) 283-1191 • 1-800-545-1191 Fax: (503) 289-7644

Website: <http://www.MalarkeyRoofing.com>**SECTION 2 - HAZARDOUS INGREDIENTS**

CAS# 64742-88-7	%Volume: 3-4%
CAS# 25551-13-7	%Volume: 8%
CAS# 64742-95-6	%Volume: 1%

Explosive Limits: LEL: 0.9%, UEL: NDA
Weight per Gallon: Approx. 7.5 lbs
%Volatile Volume: >50%,
%Water Volume: 0.0%

SECTION 3 - HAZARDS IDENTIFICATION**Emergency Overview:** This product contains asphalt. Some asphalt contains sulfur compounds which may form H₂S when heated or burnt.**Potential Health Effects:****Skin** (Route of exposure): May cause skin irritation.**Eyes:** May cause eye irritation.**Inhalation** (Route of exposure): May cause headache, nausea, throat distress.**SECTION 10 - STABILITY & REACTIVITY****Chemical Stability:** Stable under normal condition**Conditions to Avoid:** Avoid freezing, avoid high temperatures.**Incompatible Materials:** Strong Oxidants**Hazardous Decomposition Products:** CO_x, Fumes, Smoke.**Hazardous Polymerization:** May not occur**SECTION 4 - FIRST AID MEASURES****Eye:** Wash eyes with water thoroughly for 15 minutes. Call a physician.**Skin:** Wash Skin with soap and water. Do not use solvents.**Inhalation:** Move person to fresh air. Apply artificial respiration if needed.**SECTION 11 - TOXICOLOGICAL INFORMATION****Acute Toxicity:** NDA**Carcinogenicity:** The [IARC Monographs \(Vol. 35\)](#) reporting on mice painting studies states that there is sufficient evidence for the carcinogen in experimental animals of extracts of some asphalts. The same document states that there is inadequate evidence that asphalts alone are carcinogenic to humans.**SECTION 5 - FIRE FIGHTING MEASURES****Flash Point:** 110°F**Qualitative Flammable & Reactivity Properties:** Flammable**Suitable Extinguishing Media:** CO₂, Dry Chem foam**Unusual fire & explosion hazard:** Water causes fire to spread**PPE & Precautions for Fire Fighters:** Firemen should wear MSHA/NIOSH approved apparatus to protect against inhalation.**SECTION 12 - ECOLOGICAL INFORMATION****Ecotoxicity:** None**SECTION 6 - ACCIDENTAL RELEASE MEASURES****Clean Up Techniques:** Extinguish all sources of ignition. Absorb the material with clay.**Personal Precautions:** See Section 8**SECTION 14 - TRANSPORT INFORMATION****Shipping Name:** Combustible Liquid, NOS (contain mineral spirits), **labeling:** Not Required**Hazard Class:** Combustible**DOT:** Regulated, I.M.C.O>: UN (NA), #1993 Class: 3.3**SECTION 7 - HANDLING & STORAGE****Handling & Storage:** Keep storage container closed. Avoid flames & flammable material. Close air intakes on roof until solid**SECTION 15 - REGULATORY INFORMATION**

All Components of this products are on the TSCA inventory or are exempt from TSCA inventory requirements under 40 CFR 720.30

SECTION 8 - EXPOSURE CONTROLS/PERSONAL PROTECTION**Exp Limit Values:** TLV- 500ppm PEL: 100, 25, 100ppm

TLV- 5mg PEL: Nil

Engineering Controls: Do not store near flame. Use in well ventilated areas**PPE:****Eye:** Flash goggles or face shield.**Skin:** Chemical resistant gloves**Respiratory:** Not normally required**General Hygiene Considerations:** Washing facility recommended. Use proper ventilation for over exposure of the material.**SECTION 16 - OTHER INFORMATION****HMIS Rating:**

Health:	Flammability:	Reactivity:	PPE:
2	2	1	A

Note: PPE: Personal Protective Equipment

N/A: Not Applicable, NDA: No Data Available

Disclaimer:

This information is furnished without warranty, expressed or implied, except that it is accurate to the best knowledge of Malarkey Roofing Products. The data on this sheet are related only to the specific material designated herein. Malarkey Roofing Products assumes no legal responsibility for use or reliance upon these data.

SECTION 9 - PHYSICAL & CHEMICAL PROPERTIES**Boiling Range:** 310-400°F minimum**Maximum V.O.C.:** <300g/liter**Vapor Pressure:** 2mm @ 68°F**Vapor Density:** >1**Evaporation Rate:** <1