

**TECHNICAL DETAILS****COVERAGE RATE\***26.9 ft<sup>2</sup> per 1 kg  
2.5 m<sup>2</sup> per 2.3 lbs.**PACKAGING**1-kg cans  
2.3 lbs. each**FORM/COLOR**Fluid  
Gray**CATALYST CALCULATOR†****37-50°F (3-10°C)**6 scoops  
60 g**50-68°F (10-20°C)**4 scoops  
40 g**68-95°F (20-35°C)**2 scoops  
20 g**REACTION TIMES@68°F (20°C)**Pot Life: 10-15 minutes  
Rainproof: 45 minutes  
Fully Cured: 3 hours**FEATURES & BENEFITS**

- Promotes bonding to concrete, wood, and asphalt substrates
- EZ Seal membranes are monolithic, flexible and seamless
- Ideal for access-restricted areas and difficult waterproofing conditions

\* Gross yield/container is approximate. See recommendations for specific applications. Yields will vary depending upon system selected and the smoothness and absorbency of substrate.

† Measures amount of EZ Seal Catalyst required per 1 kg of primer. Scoop provided with catalyst measures 10 g. In most situations, 2 scoops of catalyst per kg of primer is satisfactory.

**EZ SEAL COMBO PRIMER****PRODUCT USE**

EZ Seal Combo Primer is a high performance, rapid-curing primer used to promote bonding of concrete, masonry, wood, asphalt cap sheet membranes, or other recommended substrates with EZ Seal liquid-applied roofing membranes. Malarkey Roofing Products® EZ Seal System is waterproof, flexible, self-adhering, and ideal for access-restricted and difficult waterproofing conditions. EZ Seal conforms and bonds directly to the substrate, eliminates the need for caulk and pitch pans, and is virtually maintenance-free.

**COMPOSITION & MATERIALS**

EZ Seal Combo Primer is a two-component, poly methyl-methacrylate resin primer. EZ Combo Primer is activated with Malarkey Roofing Products® EZ Seal Catalyst Powder (790-2).

**APPLICATION/INSTALLATION**

Before adding catalyst, pour EZ Seal Combo Primer into a second container for batch mixing and stir. Add pre-measured catalyst, mix, and stir again. Catalyze only the amount of material you can use within 10-15 minutes. Apply to substrates prepared as specified in the EZ Seal Application Instructions. Application over the primer should take place within 12 hours. Contact Malarkey's Technical Services Department for details.

**PRECAUTIONS**

EZ Seal Combo Primer is harmful by inhalation and irritating to eyes and skin. Vapors may form an explosive mixture with air so keep away from heat, flame and ignition sources. To ensure safety when handling, the user should wear appropriate PPE, including respirator in enclosed spaces. Wash thoroughly after handling. Consult SDS for complete details.

EZ Seal Combo Primer shall be stored in its original container with adequate ventilation. When not in use, keep container closed in a cool, dry location. In case of spill, absorb with liquid-binding material, collect, and dispose of waste in accordance with federal, state and local regulations. Material and container must be disposed of as hazardous waste.

**EMERGENCY INFORMATION:**

For Chemical Emergency, Spill Leak, Fire Exposure or Accident  
Call CHEMTREC Day or Night; in North America 800-424-9300

Substrates must be clean, dry, free of surface moisture, oil, grease, contaminants, and any other material or condition which would adversely effect bonding of EZ Seal to the substrate.

**WARRANTY**

Malarkey Roofing Products® offers various warranties to meet specific requirements. Contact your roofer, local distribution center or Malarkey for full details. See below for TECHNICAL ASSISTANCE contact information.

EZ Seal and other Malarkey products are available throughout North America and Pacific Rim countries.

Visit [WWW.MALARKEYROOFING.COM](http://WWW.MALARKEYROOFING.COM) for additional product information and availability.

Note: Malarkey Roofing Products® (Malarkey) inventory SKU number for this product: 754-1 EZ Seal Combo Primer

**TECHNICAL ASSISTANCE:**

Malarkey has technical services assistance available.  
Contact Malarkey for details:  
Call weekdays 7:00 am to 5:00 pm PST,  
at 800.545.1191 or 503.283.1191.  
[technicalinquiries@malarkeyroofing.com](mailto:technicalinquiries@malarkeyroofing.com)

**CORPORATE OFFICE:**

3131 N. Columbia Blvd. Telephone: 503.283.1191  
Portland, OR 97217-7472 or 800.545.1191  
P.O. Box 17217 Fax: 503.289.7644  
Portland, OR 97217-0217