

TECHNICAL DETAILS**COVERAGE RATE***

172 ft² - 287 ft² per 1 kg
16 m² - 26.7 m² per 1.75 lbs.

PACKAGING

0.8-kg cans
1.75 lbs. each

FORM/COLOR

Fluid
Colorless

CURE TIMES^Δ**1 HOUR @**

86° F
30° C

1.5 HOURS @

68° F
20° C

2 HOURS @

50° F
10° C

3 HOURS @

37° F
3° C

FEATURES & BENEFITS

- Promotes bonding to EPDM/TPO membranes
- EZ Seal membranes are monolithic, flexible and seamless
- Ideal for access-restricted areas and difficult waterproofing conditions

* Gross yield/unit is approximate. See recommendations for specific applications. Yields will vary depending upon system selected and the smoothness and absorbency of substrate.

^Δ Cure times are approximate, provided as a guideline, and may vary.

EZ SEAL EPDM/TPO PRIMER

PRODUCT USE

EZ Seal EPDM/TPO Primer is a high performance, rapid-curing primer used to promote bonding of EPDM, TPO or other approved commercial, single-ply roof membranes with EZ Seal liquid-applied roofing membranes. Malarkey Roofing Products® EZ Seal System is waterproof, flexible, self-adhering, and ideal for access-restricted and difficult waterproofing conditions. EZ Seal conforms and bonds directly to the substrate, eliminates the need for caulk and pitch pans, and is virtually maintenance-free.

COMPOSITION & MATERIALS

EZ Seal EPDM/TPO Primer is a single-component, solvent-borne (xylene), polyurethane-based primer. Like EZ Seal Metal Primer, it does not require a catalyst to activate.

APPLICATION/INSTALLATION

Lightly abrade the substrate and wipe clean. Vigorously shake container and apply primer evenly at the required consumption; avoid/remove areas of excessive application and runs at corners and angle changes. Open primer should be re-sealed immediately after use. Contact Malarkey's Technical Services Department for details.

PRECAUTIONS

EZ Seal EPDM/TPO Primer is harmful by inhalation and irritating to eyes and skin. Vapors may form an explosive mixture with air so keep away from heat, flame and ignition sources. To ensure safety when handling, the user should wear appropriate PPE, including respirator in enclosed spaces. Wash thoroughly after handling. Consult SDS for complete details.

Store EZ Seal EPDM/TPO Primer in its original container and tightly sealed in a cool, dry location. Do not leave in direct sunlight or store in temperatures above 77°F (25°C) or below 32°F (0°C). In case of spill, absorb with liquid-binding material, collect, and dispose of waste in accordance with federal, state and local regulations. Uncured resin is considered a hazardous material and must be handled as such.

EMERGENCY INFORMATION:

For Chemical Emergency, Spill Leak, Fire Exposure or Accident
Call CHEMTREC Day or Night; in North America 800-424-9300

Substrates must be clean, dry, free of surface moisture, oil, grease, contaminants, and any other material or condition which would adversely effect bonding of EZ Seal to the substrate.

WARRANTY

Malarkey Roofing Products® offers various warranties to meet specific requirements. Contact your roofer, local distribution center or Malarkey for full details. See below for TECHNICAL ASSISTANCE contact information.

EZ Seal and other Malarkey products are available throughout North America and Pacific Rim countries.

Visit WWW.MALARKEYROOFING.COM for additional product information and availability.

Note: Malarkey Roofing Products® (Malarkey) inventory SKU number for this product: 781-1 EZ Seal EPDM/TPO Primer

TECHNICAL ASSISTANCE:

Malarkey has technical services assistance available.
Contact Malarkey for details:
Call weekdays 7:00 am to 5:00 pm PST,
at 800.545.1191 or 503.283.1191.
technicalinquiries@malarkeyroofing.com

CORPORATE OFFICE:

3131 N. Columbia Blvd. Telephone: 503.283.1191
Portland, OR 97217-7472 or 800.545.1191
P.O. Box 17217 Fax: 503.289.7644
Portland, OR 97217-0217