

TECHNICAL DETAILS

COVERAGE RATE/10-KG UNIT*

134 ft² per 10 kg
12.5 m² per 22 lbs.

PACKAGING (789-8 & 789-1)

8.5-kg cans & 1.5-kg color pack
10 kg / 22 lbs. total

PACKAGING (788)

10-kg drums
22 lbs. each

FORM/COLOR (788)

Fluid
White

ALSO AVAILABLE

Custom Colors
Call for details

CATALYST CALCULATOR†

37-50°F (3-10°C)

6 scoops
60 g

50-68°F (10-20°C)

4 scoops
40 g

68-95°F (20-35°C)

2 scoops
20 g

REACTION TIMES@68°F (20°C)

Pot Life: 10-15 minutes
Rainproof: 45 minutes
Fully Cured: 3 hours

FEATURES & BENEFITS

- Used as aesthetic topcoat and sealer
- Apply smooth or with aggregate
- EZ Seal membranes are monolithic, flexible and seamless
- Ideal for access-restricted areas and difficult waterproofing conditions

* Gross yield/unit is approximate. See recommendations for specific applications. Yields will vary depending upon system selected and the smoothness and absorbency of substrate.

† Measures amount of EZ Seal Catalyst required per 1 kg of resin. Scoop provided with catalyst measures 10 g. In most situations, 2 scoops of catalyst per kg of resin is satisfactory.

**EZ SEAL FINISH
(WHITE & UNPIGMENTED)**

PRODUCT USE

EZ Seal Finish products are high performance, UV-stabilized, rapid-curing resins used as aesthetic topcoats and sealers in conjunction with liquid-applied EZ Seal roofing membranes. Malarkey Roofing Products® EZ Seal System is waterproof, flexible, self-adhering, and ideal for access-restricted and difficult waterproofing conditions. EZ Seal conforms and bonds directly to the substrate and penetrations, eliminates the need for caulk and pitch pans, and is virtually maintenance-free.

COMPOSITION & MATERIALS

EZ Seal Finish products are two-component, poly methyl-methacrylate resins, and both White (788) and Unpigmented (789-8) are activated with EZ Seal Catalyst Powder (790). Unpigmented Finish requires a 1.5-kg color pack (789-1).

APPLICATION/INSTALLATION

Before adding catalyst, thoroughly stir entire drum of EZ Seal Finish, and portion-off into a second container for batch mixing. Add pre-measured catalyst, mix, and stir again. Catalyze only the amount of material you can use within 10-15 minutes. Apply as a smooth color topcoat or with a broadcast 1.0 sand or ceramic roofing granules as directed in the EZ Seal Application Instructions. Contact Malarkey's Technical Services Department for details.

PRECAUTIONS

EZ Seal Finish resins are harmful by inhalation and irritating to eyes and skin. When mixing or applying, do not smoke and keep ignition sources away. To ensure safety when handling, the user should wear appropriate PPE, including respirator in enclosed spaces. Wash thoroughly after handling. Consult SDS for complete details.

Keep EZ Seal Finish resins tightly sealed in their original containers and store in a cool, dry location. Do not place in direct sunlight or in temperatures above 77°F (25°C) or below 32°F (0°C). Uncured resins are hazardous waste and must be handled in accordance with federal, state and local regulations. Catalyzed and cured resins may be disposed of in standard landfills.

EMERGENCY INFORMATION:

For Chemical Emergency, Spill Leak, Fire Exposure or Accident
Call CHEMTREC Day or Night; in North America 800-424-9300

Substrates must be clean, dry, free of surface moisture, oil, grease, contaminants, and any other material or condition which would adversely effect bonding of EZ Seal to the substrate.

WARRANTY

Malarkey Roofing Products® offers various warranties to meet specific requirements. Contact your roofer, local distribution center or Malarkey for full details. See below for TECHNICAL ASSISTANCE contact information.

EZ Seal and other Malarkey products are available throughout North America and Pacific Rim countries.

Visit WWW.MALARKEYROOFING.COM for additional product information and availability.

Note: Malarkey Roofing Products® (Malarkey) inventory SKU numbers for these products: 788-10 & 789-8 EZ Seal Finish

TECHNICAL ASSISTANCE:

Malarkey has technical services assistance available.
Contact Malarkey for details:
Call weekdays 7:00 am to 5:00 pm PST,
at 800.545.1191 or 503.283.1191.
technicalinquiries@malarkeyroofing.com

CORPORATE OFFICE:

3131 N. Columbia Blvd. Telephone: 503.283.1191
Portland, OR 97217-7472 or 800.545.1191
P.O. Box 17217 Fax: 503.289.7644
Portland, OR 97217-0217